

Tapizados Prestige

Características Characteristics Eigenschaften	Valor Value Ergebnis	Norma Test method Testmethode
Composición Composition Zusammensetzung	Recubrimiento: 79% PVC, 3% PU Soporte: 18% Poliéster	
Peso Weight Gewicht	450 gr/m ² ± 10%	UNI EN 222.86
Espesor Thickness Dicke	0,85 mm ± 10%	UNI EN 222.86
Ancho Width Breite	140 cm ± 10%	UNI EN 222.86
Longitud del rollo Length of roll Rollenlänge	40 m	UNI EN 222.86
Resistencia a la abrasión Abrasion resistance Verschleißwiderstand	>25.000 ciclos Martindale	ISO 12947-2
Resistencia a la luz Light fastness Lichtechtheit	4 bw	ISO 105 B02
Solidez del color al frote Color fastness to rubbing Farbechtheit gegen Reiben	Seco / Mojado: 4 GS	ISO 11640/105X12
Resistencia a la tracción Tensile strength Zugfestigkeit	Urdimbre/Warp/Kette 310 N - 100% Trama/Weft/Schluss 300 N - 95%	ISO 1421:1998
Resistencia al rasgado Tear strength Reissfestigkeit	Urdimbre/Warp/Kette min. 25 N Trama/Weft/Schluss min. 35 N	ISO 4674-1
Alargamiento a la rotura Enlongation at break Brechen Verlängerung	Urdimbre/Warp/Kette min. 90 ± 10% Trama/Weft/Schluss min. 90 ± 10%	ISO 1421
Resistencia al flexionado Flexing endurance Biegen Ausdauer	80.000 flx	ISO 5402



Normas de limpieza: Limpiar con un trapo húmedo y enjabonado. Usar sólo jabón neutro. Enjuagar con agua limpia. No usar disolventes químicos o sprays abrillantadores.
Cleaning rules: Clean with damp soapy cloth and rinse well with clean water. Do not use solvents, bleaches, synthetic detergent, polishes or aerosol spray.

Estos valores son a título indicativo y representan el promedio de varias producciones. No pueden considerarse de ningún modo vinculantes. El empleo del producto debe ser evaluado en base al uso al que se le destina. No se responde de su uso para aplicaciones impropias. Algunas pequeñas diferencias de color entre una y otra producción son admitidas.

These values are indicative and represent the average of multiple productions. They can not be considered binding in any way. The use of the product should be evaluated based on the use to which it is allocated. Not responsible for improper use applications. Some small color differences between them are admitted production.